



Ⓐ Random horizontal crack
of concrete slab / substrate

Ⓑ Rout with 1/4" diamond blade,
1/2" minimum depth

Ⓒ **SL/75™** Fill with SL/75™ joint filler,
Full Depth

Technical Office: 686 S. Adams Street Kansas City, KS 66105 (800) 321-0906	
SCALE: NTS REVISION: 9/14/2015	Random Crack Fill Method [typical detail]