

Waterborne Urethane Chemical Resistance-



ASTM D 1308 – Covered Spot Test

The information in this chart is intended to only as a guide. This information has been compiled from various sources believed to be reliable. To verify compatibility or suitability of this product in specific applications, the product should be tested under the specific service conditions. The ratings are for resistance at 77° F unless otherwise noted. Recommended Conditional means there will be some effect: swelling, discoloration, cracking, etc. Wash down within one hour of spillage to avoid effects.

Recommended Recommended/Conditional Not Recommended	R RC NR		
Test Media:	Result:		
Acetic Acid, 10%	R		
DI Water	R		
10% Sulfuric Acid	R		
10% Hydrochloric Acid	R		
14% Ammonium Hydroxide	R		
Clorox 10%/water	R		
Betadine	R		
Gasoline	R		
IPA	*RC		
50% Sodium Hydroxide	R		
MEK	*RC		
*RC – coating will recover its integrity once the chemical is removed.			