



LEGEND / KEY

- R** = Recommended
- C** = Recommended Conditionally
- N** = Not Recommended

Test Procedure: ASTM D3912 - modified 21 day immersion exposure

The information in this chart is intended only as a guide. This information has been compiled from various sources believed to be reliable. To verify compatibility or suitability of this product in specific applications, the product should be tested under the specific service conditions. The ratings are for resistance at 77°F unless otherwise noted. Recommended Conditionally means there will be some effect: swelling, discoloration, cracking. Wash down within one hour of spillage to avoid effects.

Test Media

Acetic Acid, 100%	N
Acetone	C
Ammonium Hydroxide, 20%	R
Antifreeze/Water	C
Brake Fluid (DOT 3)	C
Bromine	R
Chlorine	R
Clorox 10% / Water	C
Diesel Fuel	R
Gasoline	R
Hydrochloric Acid, 10%	C
Hydrofluoric Acid, 10%	C
Hydraulic Fluid	C
Isopropyl Alcohol	R
Lactic Acid	R
MEK	C
Methanol	C

Test Media

Motor Oil	R
MTBE	C
MTBE, 5% / Gasoline	C
Muriatic Acid, 10% HCL	R
NaCl, 10% / Water	R
Phosphoric Acid, 10%	R
Potassium Hydroxide, 10%	R
Skydrol	C
Sodium Hydroxide, 50%	R
Sodium Bicarbonate	R
Sugar / Water	R
Sulfuric Acid, 10%	R
Sulfuric Acid, 50%	C
Toluene	R
Vinegar, 5% / Water	R
Water (180°F)	R



Visit our website for more technical information and other outstanding products.

