



VF 380™

Spray Polyurea

Technical Data Sheet

686 S. Adams St. | Kansas City, KS 66105 | (913) 321-9000 | www.versaflex.com

Selection and Specification Data

Description

VersaFlex VF-380 is a 100% solids, fast setting, plural component, ultra-low shrink, polyurea elastomer and high performance coating. **VF-380** is primarily designed for foam, geotextile and other non-reinforced substrates due to its specially designed low shrink formulation, but has excellent bond to steel, concrete, masonry and other properly prepared substrates. **VF-380** is an excellent coatings solution for industrial applications requiring a resilient liner for waterproofing or secondary containment.

Ideal For:

- Foam and asbestos encapsulation
- Secondary containment
- Geotextile liners
- Water and wastewater storage ponds
- Landfills
- Solid and organic waste processing facilities

Advantages:

- Made in the USA at a ISO 9001:2015 Certified Facility
- Tough, resilient , elastomeric membrane
- Fast return to service
- Extremely low curing stress shrinkage
- Dry exposure range of -20°F to 250°F
- Installation range of -20°F to 160°F
- Excellent adhesion to concrete, masonry, and metals
- 60-Day recoat window after initial processing

Color & Stability (Limitations)

Standard colors are Black (VF1280), Tan (VF1223), Dark Gray (VF1220), and Light Gray (VF1221). Custom colors are available upon request. Note: Custom colors are not returnable; custom color options can be viewed at www.versaflex.com. The A-side (Iso) color could vary from clear to amber.

Limitations

VF-380 is an aromatic polyurea, and discoloration from exposure to ultraviolet light may occur, however, the physical properties are unaffected. **VF-380** should not be used for direct contact with extremely high or low pH levels. The installer must ensure a method for properly anchoring the geotextile fabric to the host surface.

Physical Properties (Typical) - (Post cured at 225°F for 24 hours)

Description	Method	Result
VOC (g/l)	Theoretical	0
Solid Content	Theoretical	100%
Gel Time	ASTM D1640	~25 sec.
Tack Free Time	ASTM D1640	~180 sec.
Light Traffic	ASTM D1640	120 min.
Tensile Strength	ASTM D638	3,286 psi
Elongation	ASTM D638	552%
Die C Tear Strength	ASTM D624	439 pli
100% Modulus	ASTM D638	852 psi
200% Modulus	ASTM D638	1,134 psi
300% Modulus	ASTM D638	1,471psi
Shore A Hardness	ASTM D2240	88
Shore D Hardness	ASTM D2240	42
Adhesion to Steel	ASTM D4541	> 500 psi
Adhesion to Concrete	ASTM D7234	> 200 psi ⁴

The value ranges stated in this Technical Data Sheet are based on system processing under controlled laboratory conditions. Equipment configuration and/or field application conditions may produce variances in the final system values.

Coverage Rate

VF-380 is designed for a variety of substrates and applications. Application method, substrate roughness, profile, and porosity will effect coverage rates. Always consult the specification and contract documents prior to installation.

Recommended Dry Film Thickness (Typical exposure)

Concrete:	80-100+ mils dft.
Steel (Carbon)	60-80 mils dft.
Geotextile Fabric:	60-80 mils dft.



Substrate and Surface Preparation

General

Prior to coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, and neutralized surface suitable for the specified coating. The substrate shall be free of all contaminants, such as oil, grease, rust, scale or deposits. The substrate shall be free of all dirt, dust, debris, and deleterious material. Coating performance is dependent on the degree of surface preparation.

Geotextile

Ensure geotextile is clean, dry, and free of dirt, dust, debris, or deleterious material. Only apply to the “ironed” side of geotextile. Non-woven, or spun-woven geotextiles are recommended.

Concrete & Masonry

Reference SSPC-SP 13/NACE No. 6 Surface Preparation of Concrete. Minimum surface profile equivalent to ICRI CSP3 to CSP5 in accordance with ICRI Technical Guideline No. 310.2R-2013. Maximum Moisture Content of 3 lb./24 hr./1,000 ft² per ASTM F1869 and/or less than 5% maximum moisture content per ASTM F2420.

Steel (Atmospheric/Non-Immersion Service)

Visible deposits of oil, grease, or other contaminants shall be removed according to SSPC-SP 1. Prepare in accordance with SSPC-SP6/NACE No. 3 Commercial Blast Cleaning. Provide a sharp angular anchor profile of 3.0 mil or greater.

Non-Ferrous Metals

Reference SSPC SP-16 Brush-Off Blast Cleaning of Coated and Uncoated Galvanized Steel, Stainless Steel, and Non-Ferrous Metals. Only use non-metallic blast media. Contact VersaFlex Technical Services for more information on additional substrates.

Recommended Primers	
Concrete & Masonry	VF-20
	VF-15
	Raven 175
	Raven 171FS
Carbon Steel (Optional)	PW-1
	AquataPoxy 190
Non-Ferrous Metals	PW-1
Wood & Fiberglass	VF-20
	VF-15

Note: Substrate composition and moisture, application temperature, exposure temperature, and site conditions may effect primer selection.

VersaFlex is part of a family of companies. Specific primers may be available for different substrates or service conditions.

Mixing, Thinning, and Pre-Warming

Components & Mix Ratio:

Mix ratio is 1:1 by volume

Mixing:

B Side must be mixed prior to use. Mix using a 3-tier, collapsible blade power mixer for at least 30 minutes prior to processing. Mixer diameter should be ½ diameter of the container.

Thinning:

DO NOT THIN.

Pre-warming:

A and B components should be warmed to a minimum of 70°F prior to processing.



VF 380™

Spray Polyurea

Technical Data Sheet

Application and Equipment Guidelines

General

VersaFlex VF-380 must be installed using plural component, direct impingement mix application equipment.

Recommend Equipment Operating Parameters	
A Side Primary Heat	160°F
B Side Primary Heat	160°F
Hose Heat	160°F
Dynamic Pressure	2,000—2500 psi
Dynamic Pressure Differential	< 200 psi
Inlet Pressure	> 90 psi

- Material supply capacity should be 4x the material output of the selected spray gun configuration.
- Processing equipment should be capable of maintaining set temperatures and pressures at rest and during operation.
- Proper equipment selection and maintenance is critical to achieve material properties.
- Additional equipment manufacturers and set-ups are acceptable.

Recommended Proportioners	
Graco	Reactor E-XP2
	Reactor H-XP2
	Reactor H-XP-3

Recommended Spray Gun Configuration		
Graco	Fusion AP	AR/AF 2929
		AR/AF 3737
		AR/AF 4242
	Fusion MP	XR/XF 3535
		XR/XF 4747
	Probler P2	00 - 02

Apply in a uniform manner to desired thickness. Application thickness is determined by spray gun configuration and speed of application. Lower output configurations are recommended for vertical and overhead applications to avoid runs, drips and sags. Excessive thickness does not negatively impact the material properties.

Application and Service Conditions

Environmental & Substrate Conditions

Substrate temperatures must be greater than -20°F. Lower substrate and ambient temperatures will increase the ultimate cure time.

Do not install over damp, wet, or saturated substrates. Concrete and masonry substrate moisture content shall be less than 5% when measured with a Tramex CME meter or equal. If the substrate is below freezing, traditional methods of determining moisture content are not effective. Additional steps should be taken to validate moisture readings.

The substrate must be 5°F above dew point and rising before application of coating materials.

Service Temperatures (Temperature Resistance):

Dry temperature resistance is -40°F to 250°F.

Limitations:

VF-380 is not recommended for direct contact with extremely high or low pH chemicals.

VF-380 is an aromatic based polyurea. Discoloration from exposure to ultraviolet light may occur without affecting the performance characteristics.



VF 380™
Spray Polyurea
Technical Data

Curing Schedule, Recoat Windows and Top Coats

<p>Cure Time</p> <p>Return to service is determined by ambient temperature, the service environment and exposures. Foot and light vehicle traffic can typically be allowed within 2 hrs. Full cure is achieved in 14 days at 72°F.</p> <p>Top Coating</p> <p>VF-380 can be built to the desired thickness or touched up immediately during application. VF-380 may be top-coated with non-solvent based coatings after curing for 30 minutes.</p>	<p>Recoat Time (Maximum)</p> <p>VF-380 can be recoated up to 60-days after the initial application. If the recoat window is exceeded, additional preparation is required. Before recoating over VF-380, the surface shall be clean, dry, and free of all dirt, dust, debris, and other contamination. Mechanical scarification and the use of VersaFlex Tack Coat or Raven 161 as a re-activating adhesion promoters are recommended.</p>
---	---

Cleanup and Safety

<p>Cleanup</p> <p>Cured product may be disposed of without restriction. Excess material should be mixed together and allowed to cure and disposed of in a normal manner. Product containers that are “drip free” may be disposed of according to local, state, and federal laws.</p> <p>Caution: VersaFlex VF-380 contains isocyanate. All safety precautions must be followed including proper skin protection and breathing protection. Consult SDS for proper safety suggestions.</p>	<p>Safety</p> <p>Read, understand, and follow all recommendations on the SDS. Review SDS at www.versaflex.com</p> <p>Wash thoroughly after handling, and before eating, drinking, or smoking. Have proper First Aid and PPE on site prior to opening or processing the material. Use chemical safety glasses, or goggles with splash shields. Use impervious body coverings including long sleeve clothing and boots. Use neoprene or nitrile chemical resistant gloves. Use a combination particulate filter and organic vapor respirator.</p>
--	---

Packaging, Handling, and Storage

<p>VF-380 is available in 10-gallon, 30-gallon, 60-gallon, 110-gallon, and 530-gallon kits. The containers are filled by weight.</p>	<p>Shelf Life and Storage</p> <p>One year from date of shipment, in original, unopened factory containers, stored in a sheltered area between 60°F - 80°F. Seal tightly after use to prevent introduction of moisture laden air. Store open ‘A’ side with a nitrogen cap after each use.</p>
--	---

Warranty

Limited Warranty. Company warrants its goods to be free of manufacturing defects. Goods manufactured by Company will comply with all applicable federal, state and local laws and regulations. Company makes no warranty as to any parts or equipment manufactured by others. Customer shall look solely and only to the manufacturer of such parts or equipment with respect to any warranty claims. Company hereby assigns to Customer the original manufacturer’s warranties to all such equipment and parts, to the full extent permitted. THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. SPECIFICALLY, THERE ARE NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE.

Limitation of Liability. COMPANY’S LIABILITY FOR DEFECTIVE OR NON-CONFORMING GOODS SHALL BE LIMITED TO, AND SHALL IN NO EVENT EXCEED, THE AMOUNT PAID BY CUSTOMER FOR SUCH DEFECTIVE OR NON-CONFORMING GOODS. UNDER NO CIRCUMSTANCES SHALL COMPANY BE LIABLE FOR ANY SPECIAL, PUNITIVE, INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. In no event may any claim by Customer arising from or relating to any sale of any goods or services referenced herein be brought more than one year after the date of delivery of such Goods.