



VersaFlex Incorporated  
 686 S. Adams Street  
 Kansas City, KS 66105  
 (913) 321-9000  
 (913) 321-1490 (fax)

## Material Processing & Handling Information

**Material:** VF 330

**Material Type:** Abrasion Resistant Fast Set Spray Polyurea Coating

**Application:** Concrete, Tile, CMU, Wood and other porous substrates

**Application Process:** High pressure heated equipment with impingement gun

<b>Process Equipment:</b>	<b>Pumps</b>	<b>Dispensing Gun</b>
<b>Graco:</b>	EXP-1 (Electric) EXP-2 (Electric) EXP-3 (Pneumatic) H-XP2 (Hydraulic) H-XP3 (Hydraulic)	Fusion AP (Air Purge) Fusion MP (Mechanical Purge) GX-7 Standard (Mechanical Purge) GX-8 (Mechanical Purge) Probler (Air Purge) Probler P2 (Air Purge)
<b>Gusmer:</b>	FF 2500 (Hydraulic) FF 3500 (Hydraulic) H-20/35 (Pro Hydraulic)	GX-7 Standard (Mechanical Purge) GX-7 400 (Mechanical Purge) GX-7 DI (Mechanical Purge) GX-8 (Mechanical Purge) GAP Pro (Air Purge)
<b>GlasCraft:</b>	MX, MXII (Pneumatic) MH, MHII, MHIII (Hydraulic) SuperMaxi, Guardian A Series	Probler (Air Purge) Probler P2 (Air Purge)
<b>Gama:</b>	Evolution G-250H	GDI (Mechanical)
<b>PMC:</b>	PMC GH-40 (Hydraulic)	PMC A-P2 (Air Purge)
<b>Pentech USA:</b>		PalmGun or MG Gun (low output)
<b>WIWA:</b>	DuoMix 460 (Pneumatic)	Pentech MG (Mechanical)
<b>Material Supply Pumps:</b>	<b>Pump Type</b>	<b>Continuous delivery/output at 70°F/25°C</b>
<b>Graco:</b>	Standard 2:1 (T1) Diaphragm:	Up to 1.75 gpm, 9.5 lpm
	• Husky 515	Up to 5 gpm, 26 lpm
	• Husky 716	Up to 11 gpm, 61 lpm
<b>IPM/Gusmer 2:1 (T2)</b>		Up to 3.85 gpm, 21 lpm
<b>IR/ARO (2:1)</b>	(for fluids <1000 cps)	Up to 1.4 gpm, 7.6 lpm
<b>Process Temperature:</b>	160° F optimum (150°F min, 170°F max)	
<b>Process Pressure:</b>	2,000 - 2,500 psi optimal	
<b>Gel Time:</b>	6 – 10 seconds	
<b>Tack Free:</b>	12 – 15 seconds	
<b>Light Traffic:</b>	60 - 120 minutes	
<b>Full Cure:</b>	7 days	

<b>Moisture Content:</b>	Calcium chloride test: 3 lb./24 hr./1,000 ft <sup>2</sup> Concrete: 5% maximum as per ASTM F2170 & ASTM F2420																
<b>Application Temperature:</b>	-40°F and higher  <b>VF 330</b> will cure at sub-freezing temperatures, but the effects from these conditions may impact the application in a variety of ways. It is recommended that material and equipment ambient temperatures be kept at 60°F or above. Frozen concrete substrates with high moisture content will affect coating adhesion and long-term performance.																
<b>Dew Point:</b>	Substrate temperature must be 5°F above dew point and rising before application of coating materials.																
<b>Surface Prep:</b>	Abrasive blast per ICRI Technical Guideline No. 310.2-1997 or SSPC SP13. Achieve a concrete surface profile of ICRI CSP-3 to CSP-5.																
<b>Surface contaminants:</b>	Check for soluble salts on surfaces to be coated. Test with Chlor*Test. If amount of soluble salts exceeds recommended limits, treat with Chlor*Rid. Repeat process until acceptable limits are reached. Maximum amounts of soluble salts (micrograms per square centimeter): Chlorides - 3 immersion, 7 non-immersion Nitrates - 5 immersion, 10 non-immersion Sulfates - 10 immersion, 20 non-immersion																
<b>Substrate Parging:</b>	Formed walls with honeycombing or voids/imperfections of concrete surfaces shall be repaired prior to coating.																
<b>Surface Primer:</b>	Concrete & other porous substrates: <b>VersaFlex</b> VF 15 or VF 20 (6 to 10 wet mils): Two-component sealer and primer. Follow recoat window on each.  Steel only (if required): <b>VersaFlex</b> PW-1 (2 to 3 wet mils): Single component primer. Maximum overcoat time: 24 hours, after which a light recoat is required. (1 to 2 wet mils).																
<b>Adhesion Testing:</b>	Adhesion to concrete: Minimum 150 psi. Cohesive failure of concrete is optimum. Pull values will vary depending on concrete strength.																
<b>Coating Application:</b>	Coating thickness will vary depending on intended use, surface roughness and profile. The International Concrete Repair Institute (ICRI) has developed a standard for Concrete Surface Profile (CSP) ranging between 1 (smoothest) and 9 (Roughest).  The following chart gives approximate minimum coating thickness to achieve a continuous coating using the ICRI CSP standard.  <table border="0"> <tr> <td>CSP-1 &amp; CSP-2</td> <td>45 – 55 mils</td> </tr> <tr> <td>CSP-3</td> <td>55 - 60 mils</td> </tr> <tr> <td>CSP-4</td> <td>60 – 65 mils</td> </tr> <tr> <td>CSP-5</td> <td>65 – 70 mils</td> </tr> <tr> <td>CSP-6</td> <td>70 – 75 mils</td> </tr> <tr> <td>CSP-7</td> <td>75 – 80 mils</td> </tr> <tr> <td>CSP-8</td> <td>80 - 85 mils</td> </tr> <tr> <td>CSP-9</td> <td>85 – 90 mils</td> </tr> </table> <p><b>** Please consult the VersaFlex Spray Gun Configuration Recommendation PDF for specific modules and tips.</b></p> <p><b>An 01 module is recommended for processing VF 330.</b></p>	CSP-1 & CSP-2	45 – 55 mils	CSP-3	55 - 60 mils	CSP-4	60 – 65 mils	CSP-5	65 – 70 mils	CSP-6	70 – 75 mils	CSP-7	75 – 80 mils	CSP-8	80 - 85 mils	CSP-9	85 – 90 mils
CSP-1 & CSP-2	45 – 55 mils																
CSP-3	55 - 60 mils																
CSP-4	60 – 65 mils																
CSP-5	65 – 70 mils																
CSP-6	70 – 75 mils																
CSP-7	75 – 80 mils																
CSP-8	80 - 85 mils																
CSP-9	85 – 90 mils																

	<b>Storage Temp</b>	<b>Storage</b>	<b>Special Handling</b>
<b>'A' Side</b>	60°F min. 70°F optimal	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Use dry air desiccant for intake vent on drum.
<b>'B' Side</b>	60°F min. 70°F optimal	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Mix well with mixer to re-disperse any settled pigment.
<p><b>Safety:</b> Please consult product MSDS for full details. Safety glasses, rubber gloves, protective clothing, organic vapor or fresh air respirator.</p>			