



VersaFlex Incorporated
 686 S. Adams Street
 Kansas City, KS 66105
 (913) 321-9000
 (913) 321-1490 (fax)

Material Processing & Handling Information

Material: Aquavers 405

Material Type: Fast Set Spray Polyurea Coating

Application: Concrete, Metal/Steel & other substrates

Application Process: High pressure heated equipment with impingement gun

Process Equipment:	Pumps	Dispensing Gun
Graco:	EXP-1 (Electric) EXP-2 (Electric) H-XP2 (Hydraulic) H-XP3 (Hydraulic)	Fusion AP (Air Purge) Fusion MP (Mechanical Purge) GX-7 Standard (Mechanical Purge) GX-8 (Mechanical Purge) Probler P2 (Air Purge)
Gusmer:	H 2500 (Hydraulic) H 3500 (Hydraulic) H 20/35 (Pro Hydraulic)	GX-7 Standard (Mechanical Purge) GX-7 400 (Mechanical Purge) GX-7 DI (Mechanical Purge) GX-8 (Mechanical Purge)
GlasCraft:	MX, MXII (Pneumatic) MH, MHII, MHII (Hydraulic) SuperMaxi, Guardian A Series	Probler P2 (Air Purge)
Gama:	Evolution G-250H	GDI (Mechanical)
PMC:	PMC GH-40 (Hydraulic)	PMC A-P2 (Air Purge)
Pentech USA:		PalmGun or MG Gun (low output)
WIWA:	DuoMix 460 (Pneumatic)	Pentech MG (Mechanical)
Material Supply Pumps:	<u>Pump Type</u>	<u>Continuous delivery/output at 70°F/25°C</u>
Graco:	Standard 2:1 (T1)	Up to 1.75 gpm, 9.5 lpm
	Diaphragm:	
	• Husky 515	Up to 5 gpm, 26 lpm
	• Husky 716	Up to 11 gpm, 61 lpm
IPM/Gusmer 2:1 (T2)		Up to 3.85 gpm, 21 lpm
IR/ARO (2:1)	(for fluids <1000 cps)	Up to 1.4 gpm, 7.6 lpm
Process Temperature:	150° - 160° F optimum (140°F min., 170°F max.)	
Process Pressure:	2,000 - 2,500 psi optimum (1,700 psi min., 3,500 psi max.)	
Gel Time:	8 -12 seconds	

Tack Free:	30 - 45 seconds																
Light Traffic:	60 - 120 minutes																
Moisture Content:	Calcium chloride test: 3 lb./24 hr./1,000 ft ² Concrete: 5% maximum as per ASTM F2170 & ASTM F2420																
Application Temperature:	-20°F and higher Note that Aquavers 405 will cure at sub-freezing temperatures, but the effects may impact the application in a variety of ways. It is recommended that material and equipment be kept at 60°F or above. Frozen concrete substrates with high moisture content will affect coating adhesion and long-term performance.																
Dew Point:	Substrate temperature must be 5°F above dew point and rising before application of coating materials.																
Surface Prep:	Abrasive blast per ICRI Technical Guideline No. 310.2R-2013 or SSPC SP13. Achieve a concrete surface profile of ICRI CSP-3 to CSP-5.																
Surface Contaminants:	Check for soluble salts on surfaces to be coated. Test with Chlor*Test. If amount of soluble salts exceeds recommended limits, treat with Chlor*Rid. Repeat process until acceptable limits are reached. Maximum amounts of soluble salts (micrograms per square centimeter): Chlorides - 3 immersion, 7 non-immersion Nitrates - 5 immersion, 10 non-immersion Sulfates - 10 immersion, 20 non-immersion																
Substrate Parging:	Formed walls with honeycombing/voids/imperfections of concrete surfaces shall be repaired prior to coating to eliminate surface defects.																
Concrete Primer:	VersaFlex Aquavers 20 (6 to 10 wet mils): Two-component primer. Maximum recoat window: 72 hours, after which a light recoat is required (2 to 3 wet mils).																
Adhesion Testing:	Adhesion to concrete: Minimum 150 psi. Cohesive failure of concrete is optimum. Pull values will vary depending on concrete strength.																
Coating Application:	Coating thickness will vary depending on intended use, surface roughness and profile. The International Concrete Repair Institute (ICRI) has developed a standard for Concrete Surface Profile (CSP) ranging between 1 (smoothest) and 9 (roughest). The following chart gives approximate minimum coating thickness to achieve a continuous coating using the ICRI CSP standard. <table border="0"> <tr> <td>CSP-1 & CSP-2</td> <td>45 - 55 mils</td> </tr> <tr> <td>CSP-3</td> <td>55 - 60 mils</td> </tr> <tr> <td>CSP-4</td> <td>60 - 65 mils</td> </tr> <tr> <td>CSP-5</td> <td>65 - 70 mils</td> </tr> <tr> <td>CSP-6</td> <td>70 - 75 mils</td> </tr> <tr> <td>CSP-7</td> <td>75 - 80 mils</td> </tr> <tr> <td>CSP-8</td> <td>80 - 85 mils</td> </tr> <tr> <td>CSP-9</td> <td>85 - 90 mils</td> </tr> </table> <p>** Please review the <i>Spray Gun Configuration Recommendation PDF for specific modules and tips.</i></p>	CSP-1 & CSP-2	45 - 55 mils	CSP-3	55 - 60 mils	CSP-4	60 - 65 mils	CSP-5	65 - 70 mils	CSP-6	70 - 75 mils	CSP-7	75 - 80 mils	CSP-8	80 - 85 mils	CSP-9	85 - 90 mils
CSP-1 & CSP-2	45 - 55 mils																
CSP-3	55 - 60 mils																
CSP-4	60 - 65 mils																
CSP-5	65 - 70 mils																
CSP-6	70 - 75 mils																
CSP-7	75 - 80 mils																
CSP-8	80 - 85 mils																
CSP-9	85 - 90 mils																

	Storage Temp	Storage	Special Handling
'A' Side	70°F optimum	Keep dry. Keep from freezing. Store	Use dry air desiccant for

		in covered temperature controlled environment if possible.	intake vent on drum.
'B' Side	70°F optimum	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Mix well with mixer to re-disperse any settled pigment.
Safety: Please consult product SDS for full details. Safety glasses, rubber gloves, protective clothing, organic vapor or fresh air respirator.			