



VersaFlex Incorporated
 686 S. Adams Street
 Kansas City, KS 66105
 (913) 321-9000
 (913) 321-1490 (fax)

Material Processing & Handling Information

Material: FSS 42D

Material Type: Fast Set Spray Aliphatic Polyurea Coating

Application: Concrete, Tile, CMU, Wood and other porous substrates

Application Process: High pressure heated equipment with impingement gun
 *Mechanical Purge Spray Gun provides best results & performance

Process Equipment:	Pumps	Dispensing Gun
Graco:	EXP-1 (Electric) EXP-2 (Electric) EXP-3 (Pneumatic) H-XP2 (Hydraulic) H-XP3 (Hydraulic)	Fusion AP (Air Purge) Fusion MP (Mechanical Purge) GX-7 Standard (Mechanical Purge) GX-8 (Mechanical Purge) Probler (Air Purge) Probler P2 (Air Purge)
Gusmer:	FF 2500 (Hydraulic) FF 3500 (Hydraulic) H-20/35 (Pro Hydraulic)	GX-7 Standard (Mechanical Purge) GX-7 400 (Mechanical Purge) GX-7 DI (Mechanical Purge) GX-8 (Mechanical Purge) Gap Pro (Air Purge)
GlasCraft:	MX, MXII (Pneumatic) MH, MHII, MHIII (Hydraulic) SuperMaxi, Guardian A Series	Probler (Air Purge) Probler P2 (Air Purge)
Gama:	Evolution G-250H	GDI (Mechanical)
PMC:	PMC GH-40 (Hydraulic)	PMC A-P2 (Air Purge)
Pentech USA:		PalmGun or MG Gun (low output)
WIWA:	DuoMix 460 (Pneumatic)	Pentech MG (Mechanical)
Material Supply Pumps:	<u>Pump Type</u>	<u>Continuous delivery/output at 70°F/25°C</u>
Graco:	Standard 2:1 (T1) Diaphragm:	Up to 1.75 gpm, 9.5 lpm
	• Husky 515	Up to 5 gpm, 26 lpm
	• Husky 716	Up to 11 gpm, 61 lpm
IPM/Gusmer 2:1 (T2)		Up to 3.85 gpm, 21 lpm
IR/ARO (2:1)	(for fluids <1000 cps)	Up to 1.4 gpm, 7.6 lpm
Gama:		Master Gun (Air Purge)
Process Temperature:	150 - 160°F optimum (150°F min., 190°F max.)	
Process Pressure:	2,000 - 2,500 psi optimum (1,700 psi min., 3,500 psi max.)	
Gel Time:	<1 minute	
Tack Free:	~2 minutes	

Light Traffic:	4 hours		
Moisture Content:	Calcium chloride test: 3 lb./24 hr. 1,000 ft ² Concrete: 5% maximum as per ASTM F2170 & ASTM F2420		
Application Temperature:	-30°F to 160°F		
	Note that 42D will cure at sub-freezing temperatures, but the effects may impact the application in a variety of ways. It is recommended that material and equipment ambient temperatures be kept at 60°F and above.		
Dew Point:	Substrate temperature must be 5°F above dew point and rising before application of coating materials.		
Surface Prep:	Abrasive blast per ICRI Technical Guideline No. 310.2R-2013 or SSPC SP13. Achieve a concrete surface profile of ICRI CSP-3 to CSP-5.		
Surface contaminates:	Check for soluble salts on surfaces to be coated. Test with Chlor*Test. If amount of soluble salts exceeds recommended limits, treat with Chlor*Rid. Repeat process until acceptable limits are reached. Maximum amounts of soluble salts (micrograms per square centimeter): Chlorides - 3 immersion, 7 non-immersion Nitrates - 5 immersion, 10 non-immersion Sulfates - 10 immersion, 20 non-immersion		
Substrate Parging:	Formed walls with honeycombing/voids or imperfections of concrete surfaces shall be repaired prior to coating.		
Surface Primer:	Concrete & other porous substrates: VersaFlex VF15 or VF20 (6 to 10 wet mils): Two-component sealer and primer. Steel only: VersaFlex PW-1 (2 to 3 wet mils): Single component primer. Maximum overcoat time: 24 hours, after which a light recoat is required (1 to 2 wet mils). PW-1 should only be used to hold flash rust.		
Adhesion Testing:	Adhesion to concrete: Minimum 150 psi. Cohesive failure of concrete is optimum. Pull values will vary depending on concrete strength.		
Coating Application:	Coating thickness will vary depending on intended use, surface roughness and profile. The International Concrete Repair Institute (ICRI) has developed a standard for Concrete Surface Profile (CSP) ranging between 1 (smoothest) and 10 (Roughest). The following chart gives approximate minimum coating thickness to achieve a continuous coating using the ICRI CSP standard.		
	CSP-1 & CSP-2	45 – 55 mils	
	CSP-3	55 – 60 mils	
	CSP-4	60 – 65 mils	
	Storage Temp	Storage	Special Handling
'A' Side	60°F min. 70°F optimum	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Use dry air desiccant for intake vent on drum.
'B' Side	60°F min. 70°F optimum	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Mix well with mixer to re-disperse any settled pigment.
	Safety:	Please consult product SDS for full details. Safety glasses, Rubber gloves, Protective clothing, Organic vapor or fresh air respirator.	