



VersaFlex Incorporated  
 686 S. Adams Street  
 Kansas City, KS 66105  
 (913) 321-9000  
 (913) 321-1490 (fax)

## Material Processing & Handling Information

**Material:** TopSeal  
**Material Type:** Penetrating Surface Sealer  
**Application:** Concrete or Masonry Surfaces  
**Application Process:** Spray, Roll or Brush

Process Equipment:	Pumps	Dispensing Gun
<b>Graco:</b>	390 Airless Sprayer (or similar)	FTX (or similar)
<b>Generic:</b>	Diaphragm or 1:1 Piston Pump	Use required spray gun & tips
<b>Generic:</b>	Pump-Up Sprayer	Included

<b>Process Temperature:</b>	Ambient (use above 35°F)
<b>Process Pressure:</b>	10 to 500 psi

<b>Moisture Content:</b>	Moisten slab prior to application. Saturate surface but do not allow standing water.
<b>Application Temperature:</b>	35°F and higher.
<b>Dew Point:</b>	N/A
<b>Surface Prep (as sealer only):</b>	High pressure water clean, sand, grind or abrasive blast to remove any contaminants that may interfere with penetration of <b>TopSeal</b> .
<b>Application:</b>	Apply in one or two coats using spray, roller or brush. Avoid ponding of material on horizontal surfaces.
<b>Application Rates:</b>	Concrete: 100 to 200 square feet per gallon depending on substrate porosity and surface profile. Moisten concrete prior to application, standing water should not be present.

Storage Temp	Storage	Special Handling
55°F	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Keep containers closed and protected from atmospheric contamination.

<b>Safety:</b>	Please consult product MSDS for full details.  Safety glasses, Rubber gloves, Protective clothing, Organic vapor or fresh air respirator.
----------------	---